


FACING BRICKS

PENRICE CHOCOLATE

EDENHALL



TECHNICAL DATA

SIZE	215 x 100 x 65 (+3-5mm)
DENSITY	2200kg/m ³ average
STRENGTH	22N ² /mm ² minimum average
MOISTURE ABSORPTION	6-8% typical average
DURABILITY	Fully frost resistant
FULL TECHNICAL SPECIFICATION AVAILABLE ON REQUEST	

Please Note: The colours on this data sheet are as accurate as modern printing processes will allow. You are advised to see actual brick samples before ordering.

PD EDENHALL LTD

Northern Sales 01768 483374

Central Sales 01244 677199

Southern Sales 01633 600806

EDENHALL

www.edenhall.co.uk

sales@edenhall.co.uk